

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1994  
 DateRun: 11/08/1994  
 Experimenters: Donald Garlotta  
 ClientType: Plastic Manufacturer  
 ProjectNumber: Project #1  
 Substrates: Plastic  
 PartType: Coupon  
 Contaminants: Mold Releases  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Visual

Purpose: Second attempt to remove mold release agents

Experimental Procedure: The coupons were received from the client. Two contaminants were applied to the coupons with a foam swab. One agent, Crystal 4000, was applied to the black coupon and the other contaminant, Chem Trend CT 2004, was applied to the beige coupon. Cleaning took place in an agitated wash with a 10% concentration in a beaker for fifteen minutes at 139 F. Then the coupons were rinsed in tap water for ten seconds at 146 F. A two-stage drying was used. First the parts were passed under an air knife for two minutes at ambient conditions. After the parts cooled in a desiccator to room temperature, they were inspected visually for cleanliness.

SUBSTRATE MATERIAL: Acrylate polymer coupons  
 CONTAMINANTS: Silicone mold release agents  
 CONTAMINATING PROCESS USED: Applied contaminants with foam brush swab.

Results: A good deal of mold release agent was visible on the coupons after the cleaning trial. It appeared that the cleaner and or the method selected did not work well.

Summary:

<b>Substrates:</b>	Plastic				
<b>Contaminants:</b>	Mold Releases				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Delta Omega Technologies Ltd	Attar D(R3)	10		<input type="checkbox"/>	

Conclusion: Due to insufficient cleaning, further testing must be performed to find a cleaning process.