

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002

DateRun: 02/01/2002

Experimenters: Heidi Wilcox

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Greases

Cleaning Methods: Media Blasting

Analytical Methods: Visual

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Blast coupons with CO2 crystals in room temperature. Contaminant: Formax Manufacturing Corp F-26 Grease Stick polishing lubricant (68815-16-7, 67701-27-3, 64742-52-5, 102-71-6)

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel				
<b>Contaminants:</b>		Greases				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>	
Applied Surface Technologies	CO2 Snowflakes,High Flow	100	98.76	<input checked="" type="checkbox"/>	high flow, crystal	
Applied Surface Technologies	CO2 Snowflakes, Medium Flow	100	28.85	<input type="checkbox"/>	medium flow, crystal	
Applied Surface Technologies	CO2 Snowflakes,High Flow	100	10.71	<input type="checkbox"/>	CO2 flake, high flow	
Applied Surface Technologies	CO2 Snowflakes, Low Flow			<input type="checkbox"/>		

### Conclusion: