

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003

DateRun: 03/28/2003

Experimenters: Jason Marshall

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Coatings

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F  
Drying: Wiping  
Contaminant: Ferrocote 5815 LVO

## Results:

### Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	Coatings				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
AG Environmental Products	Canola Gold CE110	100	85.91	<input checked="" type="checkbox"/>	
AG Environmental Products	Soy Gold 1000	100	87.22	<input checked="" type="checkbox"/>	
AG Environmental Products	Soy Gold 2000	100	86.41	<input checked="" type="checkbox"/>	
AG Environmental Products	Soy Clear 1500	100	79.22	<input type="checkbox"/>	
United Laboratories International	United 2002 Harvest Gold	100	89.68	<input checked="" type="checkbox"/>	
Vertec BioSolvents	VertecBio Gold Unscented Part Cleaner	100	91.83	<input checked="" type="checkbox"/>	

### Conclusion: