

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004

DateRun: 03/03/2004

Experimenters: Dave Hout

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Coatings

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Three products were used at full strength and one product was heated to 130 F on a hot plate. Twelve preweighed coupons were coated with Ferrocote 5815 LVO and allowed to dry for a half an hour and reweighed. Three coupons were cleaned in each solution for 5 minutes using stir-bar-agitation, rinsed in a tap water bath for 15 seconds at 120 F and dried using air blow off for 30 seconds at 68 F. Coupons were allowed to dry for a half an hour and then reweighed a final time. Efficiencies were calculated.

## Results:

### Summary:

<b>Substrates:</b>		Aluminum			
<b>Contaminants:</b>		Coatings			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Calgon Corporation	Geo Guard 3015	5	87.63	<input checked="" type="checkbox"/>	
ISP Technologies	Ship Shape Resin Cleaner	100	50.43	<input type="checkbox"/>	
Dow Chemical Company	XUS 40571 Development Solvent	100	93.90	<input checked="" type="checkbox"/>	
Dow Chemical Company	XUS 40579 Development Solvent	100	94.34	<input checked="" type="checkbox"/>	

Conclusion: Three of the four products were effective at removing the contaminants with an efficiency rate of >87%