

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2019

DateRun: 11/25/2019

Experimenters: Alicia McCarthy, Dan Aspach, Zoe Lawson, Rimsha Paneru

ClientType: Additive Manufacturing

ProjectNumber: Project #1

Substrates: Stainless Steel, Liquid

PartType: Part

Contaminants: Resins/Rosins

Cleaning Methods: Immersion/Soak

Analytical Methods: HSPiP

Purpose: To identify the Hansen solubility parameters of grey, grey pro, high temp, elastic, and tough resins.

Experimental Procedure: Twenty-four standardized solvents for HSPiP testing were placed into individual 22ml vials per resin. The resin was poured into a ¼ teaspoon, 1.25ml, and added to a vial; this process was repeated for each of the 24 solvents. Visual observations and ratings were taken after 15 minutes of unheated immersion. The following rating key was based on how the resin dissolved in the solvents.

Chemistries Evaluated:

(1) Toluene; (2) Dimethyl carbonate; (3) Xylenes; (4) Benzyl alcohol; (5) Ethylene glycol; (6) Methyl acetate; (7) Undecane; (8) Ethyl acetate; (9) Methanol; (10) Ethanol; (11) 1,3- Dioxolane; (12) Diethyl carbonate; (13) 1- propanol; (14) 2- propanol; (15) Propylene carbonate; (16) Thiophene; (17) 1-methoxy2-propanol; (18) Dimethyl sulfoxide; (19) Acetone; (20) 1-butanol; (21) Dimethyl glutarate; (22) Anisole; (23) 2-butoxy ethyl acetate; (24) Ethyl lactate

Results:

Solvent	Rating				
	Grey	Tough	High Temp.	Elastic	Grey Pro
1	1	2	2	0	1
2	2	2	1	2	2
3	1	2	2	0	1
4	0	0	1	2	1
5	0	0	0	2	0
6	1	2	1	2	1
7	0	0	0	0	0
8	1	2	1	1	1
9	2	2	1	0	1
10	1	0	1	1	1
11	2	2	1	2	1
12	2	0	1	2	1
13	2	0	1	1	0
14	2	0	1	2	0
15	1	2	1	2	1
16	2	2	1	1	1
17	1	0	1	2	1
18	2	0	2	1	0
19	2	2	2	0	1
20	1	0	1	1	0
21	2	0	2	2	1
22	1	2	2	2	1
23	1	0	2	1	0
24	1	2	0	2	1

Observations from Testing:

The two hardest resins to dissolve were the High Temp. Resin and the Grey Pro resin within the 10-minute cleaning time. There was no change in ratings even after a full 20 minutes of immersion. Isopropanol (#14) was not effective at dissolving the Tough and Grey Pro resin. Most of the resins settled on the bottom of the vial and agitation after rating did improve solubility with some of the solvents.

CLEANING LABORATORY EVALUATION SUMMARY

HSPIP Program Sphere Results:

A core value for D, P, and or H value of 0.25 or less is considered good, and 0.75 or higher is considered a bad.

Resin	D Value	P Value	H Value	Core Values
Grey	16.49	0.84	10.97	±[0.30, 0.65, 0.90]
Tough	18.72	10.35	15.49	±[0.35, 1.95, 0.75]
High Temp.	18.61	15.76	14.87	±[1.45, 1.15, 1.15]
Elastic	20.83	11.82	13.87	±[0.20, 0.65, 0.45]
Grey Pro.	16.51	16.67	12.86	±[0.25, 0.15, 0.30]

Summary:

Substrates:		Stainless Steel, Liquid			
Contaminants:		Resins/Rosins			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Fisher Scientific	Dimethyl glutarate (CAS:1119-40-0)			<input type="checkbox"/>	
EM Science	Toluene			<input type="checkbox"/>	
Alfa Aesar	Dimethyl Carbonate 99%			<input type="checkbox"/>	
Alfa Aesar	Methyl Acetate			<input type="checkbox"/>	
TCI America	Undecane			<input type="checkbox"/>	
Fisher Scientific	Methanol (CAS: 67-56-1)			<input type="checkbox"/>	
Fisher Scientific	Propylene carbonate 99.5% (CAS: 108-32-7)			<input type="checkbox"/>	
Alfa Aesar	Thiophene			<input type="checkbox"/>	
Fisher Scientific	Dimethyl Sulfoxide - DMSO (CAS: 67-68-5)			<input type="checkbox"/>	
Fisher Scientific	Acetone (CAS: 67-64-1)			<input type="checkbox"/>	
Alfa Aesar	1-Butanol 99.4%+			<input type="checkbox"/>	

Conclusion:

Additional solvents will be needed for testing to create a better sphere of solubility for each resin. It would also be helpful going forward to get coupons made of the resins so we can test cured and uncured at the same time. Once the spheres are considered "good", the D, P, and H values will be plugged into the software to create a junction value of all of the resins. This junction value will be used to identify the safer solvent options.