

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2019
 DateRun: 01/01/1970
 Experimenters: Sabrina Apel, Othon Pagounes
 ClientType: Medical Instrument Mfr
 ProjectNumber: Project #1
 Substrates: Titanium
 PartType: Part
 Contaminants: Oil
 Cleaning Methods: Ultrasonics
 Analytical Methods: Visual

Purpose: Five sets of 26-28 titanium parts were provided pre-contaminated with J2. Cleaners were heated to vendor recommended temperatures before immersing the parts into an ultrasonic tank for 15 minutes. Visual observations were recorded overall with notes and a set of three parts per cleaner were evaluated by three lab technicians, labelled A-C in Table 1, for cleaner and contaminant residue according using the rating key below.

Experimental Procedure: Five sets of 26-28 titanium parts were provided pre-contaminated with J2. Cleaners were heated to vendor recommended temperatures before immersing the parts into an ultrasonic tank for 15 minutes. Visual observations were recorded overall with notes and a set of three parts per cleaner were evaluated by three lab technicians, labelled A-C in Table 1, for cleaner and contaminant residue according using the rating key below.

Rating Key:

Rating Key	
1	No Residue
2	Slight Residue
3	Noticeable Residue
4	Considerable Residue
5	Severe Residue

Results:

Table 1: Visual Rating Results

Cleaner	Conc. (%)	Temp. (°F)	Before Cleaning Rating			After Cleaning Rating			Average Score
			A	B	C	A	B	C	
Dowanol PnBGE	100	100	4	5	4	2	2	1.5	2
Ozzy Juice SW 3	100	110				3	4	2.5	3
Metalnox M6386	100	130				1	1	1.5	1
Sta-Sol ESS 160	100	106				2	2	1.5	2
Liquinox	1	150				5	5	5	5

Visual Observations:

Dowanol PnBGE - Slight cleaner residue and soil residue that remained on parts after cleaning.

Ozzy Juice SW3 - Slight cleaner residue and soil residue that remained on parts after cleaning.

Metalnox M6386 - No cleaner residue or soil residue on parts after cleaning

Sta-Sol ESS-160 - No cleaner residue or soil residue on parts after cleaning, however, it took a while for the parts to completely dry

Liquinox - Cleaner residue and soil residue remained on parts after cleaning. Cleaner will need a rinse step going forward with testing.

Summary:

Substrates:	Titanium					
Contaminants:	Oil					
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	

CLEANING LABORATORY EVALUATION SUMMARY

Dow Chemical Company	Dowanol PnBGE	100%	2.00	<input checked="" type="checkbox"/>	Visual Rating
Chem Free Corporation	SW-3 Ozzy Juice (Improved Low Odor)	100%	3.00	<input type="checkbox"/>	Visual Rating
Kyzen Corporation	Metalnox M6386	100%	1.00	<input checked="" type="checkbox"/>	Visual Rating
JR Hess & Co., Inc.	Sta-Sol ESS 160	100%	2.00	<input checked="" type="checkbox"/>	Visual Rating
Alconox Inc	Liquinox	1%	5.00	<input type="checkbox"/>	Visual Rating

Conclusion:

Dowanol PnBGE, Metalnox 6386, and Sta-Sol ESS 160 were the most effective at removing J2 soil from titanium parts using heated ultrasonics.