

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2016
 DateRun: 10/26/2016
 Experimenters: John Truong, James Keats
 ClientType: Maintenance Shop
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Greases
 Cleaning Methods: Manual Wipe
 Analytical Methods: Gravimetric
 Purpose: Evaluate Troy Corp cleaners for bike soil removal

Experimental Procedure: Initial weights of the coupons were recorded. The coupons were then soiled with 1.6g of bike soil. Dirty weights were measured and they were placed in threes into the Manual SLW machine. The coupons and paper towel were both sprayed twice with the selected cleaner. 5 complete back and forth cycles were run and the coupons were then allowed to dry. Once dry, the clean weights were recorded. This process was repeated for each cleaner.

Results:	Cleaner	Initial wt of cont.	Final wt of cont.	%Cont Removed	Average %Cont Removed
	Tetra T08867	2.3976	0.0165	99.31	99.25
		2.5280	0.0175	99.31	
		2.3514	0.0204	99.13	
	Tetra T08868	2.3342	0.0689	97.05	96.70
		2.3202	0.0775	96.66	
		2.4397	0.0883	96.38	
	Tetra T08869	2.4183	0.0576	97.62	97.46
		2.4944	0.0522	97.91	
		2.4112	0.0760	96.85	
	Tetra T08870	2.3911	0.0767	96.79	96.59
		2.4295	0.0738	96.96	
		2.3840	0.0948	96.02	
	Water	2.3971	0.0695	97.10	97.92
		2.3785	0.0284	98.81	
		2.3478	0.0504	97.85	
	Tetra T08871	1.8985	0.0227	98.80	97.98
		2.0312	0.0399	98.04	
		2.0251	0.0586	97.11	
	Simple Clean	2.0251	0.0249	98.77	98.59
		2.0399	0.0199	99.02	
		2.0409	0.0415	97.97	
	Super Bike Wash	1.9874	0.0966	95.14	96.00
		2.1589	0.1372	93.64	
		2.0187	0.0156	99.23	
	WD-40 Foaming Bike Wash	2.2738	0.0539	97.63	97.55
		2.3063	0.0407	98.24	
		2.2295	0.0715	96.79	
	Goo Gone	2.0812	0.1457	93.00	93.68
		2.2908	0.1035	95.48	
		2.3270	0.1729	92.57	

Summary:	Substrates:	Stainless Steel				
	Contaminants:	Greases				
	Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:

CLEANING LABORATORY EVALUATION SUMMARY

Troy Corporation	Tetra T08867	100	99.25	<input checked="" type="checkbox"/>	
Troy Corporation	Tetra T08868	100	96.70	<input checked="" type="checkbox"/>	
Troy Corporation	Tetra T08869	100	97.46	<input checked="" type="checkbox"/>	
Troy Corporation	Tetra T08870	100	96.59	<input checked="" type="checkbox"/>	
Water	Water	100	97.92	<input checked="" type="checkbox"/>	
Troy Corporation	Tetra T08871	100	97.98	<input checked="" type="checkbox"/>	
Environmental Intelligence	Simple Green Cleaner & Degreaser	100	98.59	<input checked="" type="checkbox"/>	
Finish Line Technologies Inc	Super Bike Wash Concentrate	100	96.00	<input checked="" type="checkbox"/>	
WD 40 Company	WD 40 Foaming Bike Wash	100	97.55	<input checked="" type="checkbox"/>	
Goo Gone	Goo Gone Original	100	93.68	<input type="checkbox"/>	

Conclusion:

All the cleaners were gravimetrically effective. There was still significant residual contaminant on all cleaners besides those tested with Simple Clean and Tetra T08867.