

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2021
 DateRun: 07/11/2021
 Experimenters: Ross Goding, Edward Judge
 ClientType: Lab
 ProjectNumber: Project #4
 Substrates: Glass/Quartz, Other, Chrome
 PartType: Coupon
 Contaminants: Glass
 Cleaning Methods: Manual Wipe
 Analytical Methods: Gravimetric, Visual

Purpose: To test the effectiveness of Lysol All Purpose in the removal of Glass Soil from various substrates.

Experimental Procedure: A Lysol All Purpose Cleaner solution was gathered to begin testing. Then, 3 coupons of each substrate (chrome, glass, mirror) were collected and initial weights were taken. SSL Soil 2 Glass Soil was applied to each coupon and allowed to air dry for 24 hours. After the 24 hour dry time, the weights of the newly contaminated coupons were measured. All coupons were placed into a Gardner-scrub Abrasion Tester machine. Wypall cleaning cloths were attached to each of the 3 cleaning blocks used for the test. Each Wypall cloth and all coupons received 2 sprays of the Lysol All Purpose Cleaner solution and the Gardner-scrub Abrasion Tester was run for 20 repetitions, simulating 20 manual wipes. Once cleaning concluded, the cleaned coupons were allowed to air dry for 24 hours. After 24 hours, the weights of the cleaned coupons were measured.

Results:

Cleaner	Substrate	Initial wt of cont.	Final wt of cont.	%Cont Removed	% AVG	% Overall
Lysol All Purpose	Chrome	0.0315	0.0014	95.56	77.47	75.89
		0.0432	0.0025	94.21		
		0.0520	0.0384	26.15		
	Glass	0.0297	0.0018	93.94	78.76	
		0.0193	0.0022	88.60		
		0.0322	0.0149	53.73		
	Mirror	0.0319	0.0033	89.66	71.44	
		0.0192	0.0033	82.81		
		0.0258	0.0150	41.86		

Summary:

Substrates:		Glass/Quartz, Other, Chrome				
Contaminants:		Glass				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	
Reckitt Benckiser	Lysol All-Purpose Cleaner	100%	75.89	<input type="checkbox"/>	Lysol All-Purpose Cleaner was not effective in the removal of Glass Soil from various substrates.	

Conclusion:

Lysol All Purpose Cleaner was successful in removing Glass Soil from chrome, glass, and mirror substrates.