

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1998  
 DateRun: 09/17/1998  
 Experimenters: Jason Marshall  
 ClientType: Aerospace Industry  
 ProjectNumber: Project #1  
 Substrates: Alloys, Nickel  
 PartType: Part  
 Contaminants: Cutting/Tapping Fluids, Lubricating/Lapping Oils, Oil  
 Cleaning Methods: Ultrasonics  
 Analytical Methods: Black light  
 Purpose: Further comparison of current cleaner with two alternative products.

Experimental Procedure: Parts were immersed into a beaker containing the oil. Observations were made under black light conditions to determine a baseline level of fluorescence. The two successful chemistries from the previous trial and the client supplied cleaner were made into 15% solutions using DI water in 600 mL beakers. The beakers were placed into a 40 kHz Crest ultrasonic unit model 4Ht 1014-6 and heated to 150 F. One part was placed into each beaker and cleaned for 3 minutes without the ultrasonic unit working. Parts were inverted and cleaned for another 3 minutes using the ultrasonic energy. Each part was removed and rinsed with tap water at 120 F for 20 seconds and dried with a Master Appliance Heat Gun model HG-301A. Black light observations were made and recorded.

SUBSTRATE MATERIAL: Nickel Alloy-Inconel  
 CONTAMINANTS: Oil--Zyglo Penetrant ZL-27A

Results: All three chemistries removed almost all of the oil from the parts. Table 1 lists the cleaner, observations and ranking.

Table 1. Comparison of Chemistries

CHEMISTRY	OBSERVATIONS	RANKING (1 = Best, 3 = Worst)
Blue Gold	Lots of oil seeping out of holes	3
Valtech	Some oil seeping out of holes	1
SWR One	Moderate amount of oil seeping out of holes	2

The results were consistent with the previous testing except for one condition. The amount of oil remaining on the parts was higher during this trial than in the previous testing. The ratings remained the same with Valtech product cleaning the best.

Summary:

<b>Substrates:</b>	Alloys, Nickel				
<b>Contaminants:</b>	Cutting/Tapping Fluids, Lubricating/Lapping Oils, Oil				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Carroll Company	Blue Gold Heavy Industrial Cleaner	15		<input type="checkbox"/>	
Valtech Corporation	Valtron SP 2275	15		<input checked="" type="checkbox"/>	
SWR Corporation	SWR One	15		<input checked="" type="checkbox"/>	

Conclusion: Two cleaners, Valtech and SWR One, were determined to clean as well as the client's current cleaner. Next test will be conducted using the EDM fluid.