

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1998  
 DateRun: 09/10/1998  
 Experimenters: Jason Marshall, Prashant Trivedi  
 ClientType: Name Plate Mfg-Etching  
 ProjectNumber: Project #1  
 Substrates: Aluminum  
 PartType: Part  
 Contaminants: None  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric, Visual, Wipe

Purpose: To determine if second cleaner from previous trial will remove the paint.

Experimental Procedure: Initial weights of 3 customer-supplied coupons were recorded. The cleaning solution was used at 100% solution and room temperature. Three coupons were placed in each cleaning chemistry. After soaking for 24 hours, the coupons were removed from the cleaner and wiped dry with a white paper towel. Observations were made during the wiping to determine if any of the paint was removed.  
 SUBSTRATE MATERIAL: Aluminum 3003 with paint (not to be removed)  
 CONTAMINANTS: None

Results: Wiping the coupons with the paper towel revealed that some of the paint was removed during the soaking. It was also noted that the coupons had a slick feeling to them, indicating that some of the cleaner remained on the surface of the coupons. Most of this slickness was removed after the wiping was repeated.  
 The gravimetric analysis in Table 1 shows that there was some weight increase for each of the 3 coupons. This weight gain was far less than the previous experiment with the Chrisal product.

Table 1. Gravimetric Analysis Results

Coupon #	Initial Weight	Final Weight	Weight Gain	% Increase
7	11.3966	11.404	0.0074	0.065
8	11.2904	11.2979	0.0075	0.066
9	11.3977	11.4085	0.0108	0.095

Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	None				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
AG Environmental Products	Soy Gold 1000	100		<input checked="" type="checkbox"/>	

Conclusion:

All 9 coupons from the trials on the supplied coupons have been returned for further analysis to the client. The Soy Gold-cleaned parts should be examined to determine if the residue will effect further processing steps.  
 NOTE:  
 Coupons 1,2,3 are from the 5% Chrisal Test  
 Coupons 4,5,6 are from the 100% Chrisal Test  
 Coupons 7,8,9 are from the Soy Gold Test