

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2004  
 DateRun: 05/06/2004  
 Experimenters: Jason Marshall  
 ClientType: Jewelry Mfr  
 ProjectNumber: Project #2  
 Substrates: Sterling/Silver  
 PartType: Coupon  
 Contaminants: Oil  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: To evaluate products on fourth supplied contaminant

**Experimental Procedure:** Seven products were selected based on success in previous two trials as well as three new products. The seven products were used at full strength in a 250 ml beaker and heated to 96 F on a hot plate. The new products were used at room temperature due to lower flash points. Thirty preweighed silver plated copper coupons were coated with the Houghton International Cindol 3401 oil (64742-46-7) using a hand held swab. Coupons were weighed a second time to determine the amount of soil added to each coupon. Three coupons were cleaned in each solution for 5 minutes using stir-bar agitation. After cleaning parts were weighed a final time and efficiencies were calculated.

**Results:** All ten products remove over 93% of the oil within five minutes of cleaning. Seven removed over 98% and four removed over 99%. The table lists the amount of soil added, the amount remaining and the efficiency for each coupon cleaned.

Cleaner	Initial wt	Final wt	% Removed
HFE 7100	0.0489	0.0006	98.77
	0.0637	0.0004	99.37
	0.0590	0.0018	96.95
AK 225	0.0718	0.0048	93.31
	0.0651	0.0046	92.93
	0.0651	0.0032	95.08
Vertrel CCA	0.0922	0.0009	99.02
	0.0461	0.0009	98.05
	0.0872	0.0005	99.43
Ensolv	0.0858	0.0031	96.39
	0.0358	0.0029	91.90
	0.0769	0.0032	95.84
Metalnox M6760	0.0624	0.0014	97.76
	0.0760	0.0013	98.29
	0.0398	0.0000	100.00
Solvon PB	0.0391	0.0001	99.74
	0.1009	0.0002	99.80
	0.0443	-0.0001	100.23
Solvon IP	0.0803	0.0004	99.50
	0.0791	0.0001	99.87
	0.0410	-0.0002	100.49
OS 10	0.0797	0.0004	99.50
	0.0922	0.0005	99.46
	0.1000	-0.0003	100.30
OS 20	0.0649	-0.0006	100.92
	0.0976	-0.0005	100.51
	0.0644	-0.0006	100.93
OS 30	0.0376	0.0033	91.22
	0.1002	0.0055	94.51
	0.0533	0.0009	98.31

Summary:

<b>Substrates:</b>	Sterling/Silver
--------------------	-----------------

## CLEANING LABORATORY EVALUATION SUMMARY

<b>Contaminants:</b>		Oil			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
3M	HFE 7100	100	98.36	<input checked="" type="checkbox"/>	
AGA Chemical	AK 225	100	93.78	<input checked="" type="checkbox"/>	
DuPont	Vertrel CCA	100	98.83	<input checked="" type="checkbox"/>	
Enviro Tech International Inc	Ensolv	100	94.71	<input checked="" type="checkbox"/>	
Kyzen Corporation	Metalnox M6960	100	98.68	<input checked="" type="checkbox"/>	
Poly Systems USA Inc	Solvon Kreussler PB	100	99.92	<input checked="" type="checkbox"/>	
Poly Systems USA Inc	Solvon Kreussler IP	100	99.95	<input checked="" type="checkbox"/>	
Dow Chemical Company	OS 10	100	99.75	<input checked="" type="checkbox"/>	
Dow Chemical Company	OS 20	100	100.79	<input checked="" type="checkbox"/>	
Dow Chemical Company	OS 30	100	94.68	<input checked="" type="checkbox"/>	

Conclusion: A follow up trial will be conducted on the first contaminant to evaluate five products.