

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003
 DateRun: 02/25/2003
 Experimenters: Jason Marshall, Heidi Wilcox
 ClientType: State Agency
 ProjectNumber: Project #2
 Substrates: Ceramics, Fiberglass, Chrome
 PartType: Coupon
 Contaminants: Soaps
 Cleaning Methods: Manual Wipe
 Analytical Methods: Gravimetric, Photography
 Purpose: To evaluate newly supplied cleaner on SSL Soil 1 on three substrates

Experimental Procedure: One supplied cleaning product was diluted to vendor recommended concentrations for bathroom cleaning. The product was diluted with DI water. Three preweighed fiberglass, three ceramic and three chrome coupons were coated with SSL Soil 1 (Bathroom soap scum: Vaseline Dry Skin Lotion 21.4%, Dial Clean Rinsing Body Wash 14.3%, Market Basket Shampoo & Conditioner (Pert) 28.6%, Soft Soap Natural Liquid hand soap 21.4%, Coast Deodorant bar soap 7.2% and Water 7.1%) using a hand held swab and allowed to dry for 24 hours at room temperature. The contaminated coupons were weighed again to determine the amount of soil added. Photographs were taken.

Three coupons were placed into a Gardner Straight Line Washability unit. A Professional Painter's Rag was attached to the cleaning sled and soaked with 5-7 sprays of cleaning solutions. Each coupon was sprayed 7-10 times with the same cleaning solution. The cleaning unit was run for 20 cycles (~33 seconds). At the end of the cleaning, coupons were wiped once with a dry paper towel. Final weights were recorded and a second set of photographs were taken. Efficiencies were calculated and recorded.

Results: The product was successful in removing SSL Soil 1 from fiberglass, ceramic and chrome coupons. Table 1 lists the amount of soil applied and removed.
 Table 1. Soil Application and Removal

| Cleaner | Initial wt | Final wt | % Removed |
|------------|------------|----------|-----------|
| Fiberglass | 0.1281 | 0.0046 | 96.41 |
| | 0.0930 | 0.0022 | 97.63 |
| | 0.0845 | 0.0037 | 95.62 |
| Ceramic | 0.0766 | 0.0005 | 99.35 |
| | 0.0692 | 0.0015 | 97.83 |
| | 0.0364 | -0.0004 | 101.10 |
| Chrome | 0.0627 | 0.0042 | 93.30 |
| | 0.0629 | 0.0079 | 87.44 |
| | 0.0557 | 0.0049 | 91.20 |

Summary:

| | | | | | | |
|--------------------------|---|------------------------------|--------------------|-------------------------------------|----------------------|--|
| Substrates: | | Ceramics, Fiberglass, Chrome | | | | |
| Contaminants: | | Soaps | | | | |
| Company Name: | Product Name: | Conc.: | Efficiency: | Effective: | Observations: | |
| The Clean Environment Co | N-7 (the Natural) Basin, Tub and Tile Cleaner | 33 | 96.55 | <input checked="" type="checkbox"/> | Fiberglass | |
| The Clean Environment Co | N-7 (the Natural) Basin, Tub and Tile Cleaner | 33 | 99.43 | <input checked="" type="checkbox"/> | Ceramic | |
| The Clean Environment Co | N-7 (the Natural) Basin, Tub and Tile Cleaner | 33 | 90.65 | <input checked="" type="checkbox"/> | Chrome | |

Conclusion: The second product from this vendor will be used on SSL Soil 2 on glass and chrome surfaces.