

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999
 DateRun: 07/08/1999
 Experimenters: Nicole Vayo
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Inks
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Four products were diluted to 5% and heated to 130 F. Stainless steel coupons were coated with Cerdec Magenta Ink (20667-12-3, 1345-24-0, 65997-18-4, 119-18-4).
 Results: Both contaminant and solutions are smelly. The contaminant: paint. The solutions: soap.

Summary:

Substrates:	Stainless Steel				
Contaminants:	Inks				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Oakite Products	Oakite Low Heat Cleaner 1	5	14.00	<input type="checkbox"/>	
Man Gill Chemical Company	Gillite 1156	5	13.00	<input type="checkbox"/>	
Calgon Corporation	RT 806	5	15.00	<input type="checkbox"/>	
Heatbath Corporation	Uni Kleen 10	5	14.00	<input type="checkbox"/>	

Conclusion: No product removed over 20%