

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999
 DateRun: 07/11/1999
 Experimenters: Nicole Vayo
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Aluminum, Brass, Copper, Glass/Quartz, Stainless Steel
 PartType: Coupon
 Contaminants: Oil
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: One product was used at 5% and heated to 122 F. Brass, stainless steel, aluminum, copper and glass coupons wer coated with an oil (64741-89-5)

Results:

Summary:

Substrates:	Aluminum, Brass, Copper, Glass/Quartz, Stainless Steel				
Contaminants:	Oil				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Savogran Company	Dirtex Prepaint Cleaner	5	101.00	<input checked="" type="checkbox"/>	on brass
Savogran Company	Dirtex Prepaint Cleaner	5	101.00	<input checked="" type="checkbox"/>	on stainless steel
Savogran Company	Dirtex Prepaint Cleaner	5	102.00	<input type="checkbox"/>	on aluminum
Savogran Company	Dirtex Prepaint Cleaner	5	101.00	<input checked="" type="checkbox"/>	on copper
Savogran Company	Dirtex Prepaint Cleaner	5	101.00	<input checked="" type="checkbox"/>	on glass

Conclusion: Efficiencies were all over 100%. Damage occurring?