

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999  
 DateRun: 07/12/1999  
 Experimenters: Nicole Vayo  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Aluminum, Brass, Copper, Stainless Steel  
 PartType: Coupon  
 Contaminants: Oil  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: One product was diluted to 5% and heated to 130 F. Aluminum, brass, copper and stainless steel coupons were coated with an oil (64741-89-5)  
 Results: Oil is lifted into solution, covered in a white foam until dispersed. A control was used to verify scale analysis. Percent efficiency is consistent for any substrate used.

Summary:

<b>Substrates:</b>	Aluminum, Brass, Copper, Stainless Steel				
<b>Contaminants:</b>	Oil				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Man Gill Chemical Company	Gillite 160 X	5	100.00	<input checked="" type="checkbox"/>	on aluminum
Man Gill Chemical Company	Gillite 160 X	5	100.00	<input checked="" type="checkbox"/>	on brass
Man Gill Chemical Company	Gillite 160 X	5	101.00	<input checked="" type="checkbox"/>	on copper
Man Gill Chemical Company	Gillite 160 X	5	100.00	<input checked="" type="checkbox"/>	on stainless steel

Conclusion: Effective on all four surfaces.