

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999

DateRun: 07/30/1999

Experimenters: Nicole Vayo

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Greases, Inks, Oil

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Two products were used at 50%, 12%, 10% and 25%. Stainless steel coupons were coated with an oil (64741-89-5), a grease (64742-47-8) and an ink (67-63-0, 108-88-3, 9004-70-0, 109-60-4, 64-17-5, 141-78-6)

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel			
<b>Contaminants:</b>		Greases, Inks, Oil			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Chemtronics Inc	Super Bio Wash	10	96.90	<input checked="" type="checkbox"/>	grease
Chemtronics Inc	Super Bio Wash	10	68.50	<input type="checkbox"/>	oil
Chemtronics Inc	Super Bio Wash	50	7.97	<input type="checkbox"/>	ink
Diversey Corporation	Gangbusters	10	80.70	<input type="checkbox"/>	oil
Diversey Corporation	Gangbusters	10	98.97	<input checked="" type="checkbox"/>	grease
Diversey Corporation	Gangbusters	25	4.50	<input type="checkbox"/>	ink

Conclusion: Most success on the grease.