

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999
 DateRun: 07/29/1999
 Experimenters: Nicole Vayo
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Greases, Inks, Oil
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Two products were used at 50%, 12%, 10% and 25%. Stainless steel coupons were coated with an oil (64741-89-5), a grease (64742-47-8) and an ink (67-63-0, 108-88-3, 9004-70-0, 109-60-4, 64-17-5, 141-78-6)

Results:

Summary:

Substrates:		Stainless Steel			
Contaminants:		Greases, Inks, Oil			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Chemtronics Inc	Super Bio Wash	10	96.90	<input checked="" type="checkbox"/>	grease
Chemtronics Inc	Super Bio Wash	10	68.50	<input type="checkbox"/>	oil
Chemtronics Inc	Super Bio Wash	50	7.97	<input type="checkbox"/>	ink
Diversey Corporation	Gangbusters	10	80.70	<input type="checkbox"/>	oil
Diversey Corporation	Gangbusters	10	98.97	<input checked="" type="checkbox"/>	grease
Diversey Corporation	Gangbusters	25	4.50	<input type="checkbox"/>	ink

Conclusion: Most success on the grease.