

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999
 DateRun: 08/09/1999
 Experimenters: Nicole Vayo
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Copper, Nickel, Stainless Steel
 PartType: Coupon
 Contaminants: Coatings, Inks
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Coating, CAS: 64742-52-5, 64742-47-8
 Ink, CAS: 67-63-0, 108-88-3, 9004-70-0, 109-60-4, 141-78-6, 64-17-5

Results:

Summary:

Substrates:	Copper, Nickel, Stainless Steel				
Contaminants:	Coatings, Inks				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Environmental Services	TASC	5	66.40	<input type="checkbox"/>	coating, copper
Environmental Services	TASC	5	36.20	<input type="checkbox"/>	ink, copper
Man Gill Chemical Company	Gillite 1156	5	99.30	<input checked="" type="checkbox"/>	coating, copper
Man Gill Chemical Company	Gillite 1156	5	37.40	<input type="checkbox"/>	ink, copper
Oakite Products	Oakite 77	5	89.10	<input checked="" type="checkbox"/>	coating, ss
Oakite Products	Oakite Low Heat Cleaner 1	5	97.50	<input checked="" type="checkbox"/>	coating, ss
Oakite Products	Oakite Low Heat Cleaner 1	5	39.20	<input type="checkbox"/>	ink, ss
Calgon Corporation	RT 806	5	95.20	<input checked="" type="checkbox"/>	coating, ss
Calgon Corporation	RT 806	5	33.99	<input type="checkbox"/>	ink, ss
Heatbath Corporation	Uni Kleen 10	5	98.80	<input checked="" type="checkbox"/>	coating, copper
Heatbath Corporation	Uni Kleen 10	5	35.50	<input type="checkbox"/>	ink, copper

Conclusion: