

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 1999  
 DateRun: 08/10/1999  
 Experimenters: Nicole Vayo  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Copper, Nickel, Stainless Steel  
 PartType: Coupon  
 Contaminants: Adhesive, Greases, Inks, Lubricating/Lapping Oils, Oil  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning. Laboratory evolution.  
 Contaminant: Oil, CAS: 64741-89-5  
 Lubricant, CAS: 64742-47-8, 9003-29-6  
 Ink, CAS: 67-63-0, 108-88-3, 9004-70-0, 109-60-4, 141-78-6, 64-17-5  
 Grease, CAS: 64742-47-8  
 Adhesive, CAS: 9010-98-4, 65997-13-9, 68083-03-4, 108-88-3, 67-56-1, 1314-13-2, 117-47-1, 8052-10-6  
 Results: 10% lifted adhesive, got peeled off during hook removal. Beaded up lubricant to top within first 2 minutes. Active foaming action on grease.

Summary:

<b>Substrates:</b>	Copper, Nickel, Stainless Steel				
<b>Contaminants:</b>	Adhesive, Greases, Inks, Lubricating/Lapping Oils, Oil				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Safe Science Inc	Safe Science Concrete/Graffiti (Industrial)	100	101.98	<input checked="" type="checkbox"/>	oil, copper
Safe Science Inc	Safe Science Concrete/Graffiti (Industrial)	100	101.70	<input checked="" type="checkbox"/>	lubricant
Safe Science Inc	Safe Science Concrete/Graffiti (Industrial)	100	37.00	<input type="checkbox"/>	ink
Safe Science Inc	Safe Science Concrete/Graffiti (Industrial)	100	66.10	<input type="checkbox"/>	grease
Safe Science Inc	Safe Science Concrete/Graffiti (Industrial)	100	86.00	<input checked="" type="checkbox"/>	adhesive
Safe Science Inc	Safe Science All Purpose (Industrial)	10	77.80	<input type="checkbox"/>	oil, ss
Safe Science Inc	Safe Science All Purpose (Industrial)	10	79.50	<input type="checkbox"/>	lubricant
Safe Science Inc	Safe Science All Purpose (Industrial)	10	74.50	<input type="checkbox"/>	ink
Safe Science Inc	Safe Science All Purpose (Industrial)	10	94.30	<input checked="" type="checkbox"/>	grease
Safe Science Inc	Safe Science All Purpose (Industrial)	10	96.00	<input checked="" type="checkbox"/>	adhesive

Conclusion: