

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2000

DateRun: 06/09/2000

Experimenters: Nicole Vayo

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum, Brass, Copper, Nickel, Stainless Steel

PartType: Coupon

Contaminants: Adhesive, Fluxes, Greases, Inks, Oil

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Laboratory evaluation.  
Contaminant: Adhesive, Acrylic Sealant 5504  
Flux, Ersin 5381 RMA  
Ink, CAS: 67-63-0, 108-88-3, 9004-70-0, 109-60-4, 141-78-6, 64-17-5  
Grease, CAS: 64742-47-8  
Oil, CAS: 64741-89-5, 8052-42-4

## Results:

### Summary:

<b>Substrates:</b>		Aluminum, Brass, Copper, Nickel, Stainless Steel			
<b>Contaminants:</b>		Adhesive, Fluxes, Greases, Inks, Oil			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Transene Company, Inc.	D Greeze 1000	100	90.00	<input checked="" type="checkbox"/>	flux
Transene Company, Inc.	D Greeze 1000	100	14.00	<input type="checkbox"/>	ink
Transene Company, Inc.	D Greeze 1000	100	127.00	<input type="checkbox"/>	grease
Transene Company, Inc.	D Greeze 1000	100	99.00	<input checked="" type="checkbox"/>	oil
Transene Company, Inc.	D Greeze 1000	100	24.00	<input type="checkbox"/>	adhesive
Transene Company, Inc.	D-Greeze GL 46	5	96.00	<input type="checkbox"/>	oil
Transene Company, Inc.	D-Greeze GL 55	5	87.00	<input checked="" type="checkbox"/>	oil

### Conclusion: