

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2000  
 DateRun: 07/15/2000  
 Experimenters: John Brunelle  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Liquid  
 PartType: Coupon  
 Contaminants: Adhesive  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Visual  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Laboratory evaluation.  
 Contaminant: Adhesive  
 Results: Poor<Fair<Okay<Good<Excellent

Summary:

<b>Substrates:</b>	Liquid				
<b>Contaminants:</b>	Adhesive				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Westford Chemical Corporation	Biosolve	100		<input type="checkbox"/>	Poor
Bio Chem Systems	Bio T Max	100		<input type="checkbox"/>	Fair
Dysol	DS 104 Wipe Solvent	100		<input type="checkbox"/>	Fair/okay
EcoLink	Safe Strip	100		<input checked="" type="checkbox"/>	Okay
Savogran Company	SI #8 Coating Remover	100		<input type="checkbox"/>	Fair
Transene Company, Inc.	D Greeze 500 LO	100		<input type="checkbox"/>	Fair
Gemtek Products	SC Supersolve Safety Solvent	100		<input type="checkbox"/>	Poor/fair
Today & Beyond	Beyond 2009	100		<input type="checkbox"/>	Poor/fair

Conclusion: Five products were found to be fair to okay for dissolving the adhesive.