

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 06/26/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum, Steel

PartType: Coupon

Contaminants: Adhesive, Coatings, Inks

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Adhesive, Ideal Tape AC059, CAS: 108-88-3
Coating, Heraeus Covercoat L406, CAS: 85-68-7, 108-67-8
Ink, Tough Tex

Results:

Summary:

Substrates:	Aluminum, Steel				
Contaminants:	Adhesive, Coatings, Inks				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Warren Chemical Company	Sea Wash 8	5	35.80	<input type="checkbox"/>	coating
Warren Chemical Company	Sea Wash 8	5	1.18	<input type="checkbox"/>	ink
CRC Industries	Complex Blue	5	36.05	<input type="checkbox"/>	coating
CRC Industries	Complex Blue	5	0.72	<input type="checkbox"/>	ink
Bio Chem Systems	Bio T 200 A	100	45.32	<input type="checkbox"/>	adhesive
Bio Chem Systems	Bio T 200 A	100	39.30	<input type="checkbox"/>	ink

Conclusion: