

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 07/18/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Coatings

Cleaning Methods: Ultrasonics

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Laboratory evaluation.  
Contaminant: Coating, Heraeus Covercoat L406, CAS: 85-68-7, 108-67-8

Results:

Summary:

<b>Substrates:</b>		Stainless Steel				
<b>Contaminants:</b>		Coatings				
<b>Company Name:</b>		<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
International Bio System		Bio Z	10	41.30	<input type="checkbox"/>	
Heatbath Corporation		Uni Kleen 10	4	40.60	<input type="checkbox"/>	
Heatbath Corporation		MultiKleen LX 1573	5	38.60	<input type="checkbox"/>	
Innovative Organics Inc		Amberclean SC 11	5	41.70	<input type="checkbox"/>	
MacDermid Industrial Products		New Dimensions LF Supreme	4	40.90	<input type="checkbox"/>	

Conclusion: