

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 07/24/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Aluminum
 PartType: Coupon
 Contaminants: Lubricating/Lapping Oils
 Cleaning Methods: Immersion/Soak
 Analytical Methods:
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Lubricant, Keystone Nevastone 6, CAS: 64742-47-8, 8042-47-5, 9003-29-6

Results:

Summary:

Substrates:	Aluminum				
Contaminants:	Lubricating/Lapping Oils				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Transene Company, Inc.	D Greeze 500 LO	100	98.40	<input checked="" type="checkbox"/>	
Inland Technologies Inc	EP 921	100	98.80	<input checked="" type="checkbox"/>	
Buckeye International	Shopmaster	20	91.02	<input checked="" type="checkbox"/>	
Safe Science Inc	Safe Science Engine Degreaser (Industrial)	100	101.00	<input checked="" type="checkbox"/>	

Conclusion: