

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 07/23/2001  
 Experimenters: Ravi Krishnappa  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Aluminum  
 PartType: Coupon  
 Contaminants: Lubricating/Lapping Oils  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods:  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Laboratory evaluation.  
 Contaminant: Lubricant, Keystone Nevastone 6, CAS: 64742-47-8, 8042-47-5, 9003-29-6

Results:

Summary:

<b>Substrates:</b>	Aluminum				
<b>Contaminants:</b>	Lubricating/Lapping Oils				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Transene Company, Inc.	D Greeze 500 LO	100	98.40	<input checked="" type="checkbox"/>	
Inland Technologies Inc	EP 921	100	98.80	<input checked="" type="checkbox"/>	
Buckeye International	Shopmaster	20	91.02	<input checked="" type="checkbox"/>	
Safe Science Inc	Safe Science Engine Degreaser (Industrial)	100	101.00	<input checked="" type="checkbox"/>	

Conclusion: