

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 08/09/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Steel
 PartType: Coupon
 Contaminants: Waxes
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Paraffin Wax

Results:

Summary:

Substrates:	Steel				
Contaminants:	Waxes				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Emkay Chemical Company	Safety Wash	25	-0.81	<input type="checkbox"/>	
Emkay Chemical Company	Safety Wash CRC	25	-0.56	<input type="checkbox"/>	
Emkay Chemical Company	Safety Wash Clear	25	-0.62	<input type="checkbox"/>	
US Polychem Corporation	87 RB	100	64.00	<input type="checkbox"/>	
Gemtek Products	SC 1000 Aqueous Cleaner Concentrate	25	-1.03	<input type="checkbox"/>	
Alconox Inc	Citranox	3	0.19	<input type="checkbox"/>	

Conclusion: