

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 08/09/2001  
 Experimenters: Ravi Krishnappa  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Steel  
 PartType: Coupon  
 Contaminants: Waxes  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Laboratory evaluation.  
 Contaminant: Paraffin Wax

## Results:

### Summary:

<b>Substrates:</b>	Steel				
<b>Contaminants:</b>	Waxes				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Emkay Chemical Company	Safety Wash	25	-0.81	<input type="checkbox"/>	
Emkay Chemical Company	Safety Wash CRC	25	-0.56	<input type="checkbox"/>	
Emkay Chemical Company	Safety Wash Clear	25	-0.62	<input type="checkbox"/>	
US Polychem Corporation	87 RB	100	64.00	<input type="checkbox"/>	
Gemtek Products	SC 1000 Aqueous Cleaner Concentrate	25	-1.03	<input type="checkbox"/>	
Alconox Inc	Citranox	3	0.19	<input type="checkbox"/>	

### Conclusion: