

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 08/17/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Coatings

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Laboratory evaluation.
Contaminant: Coating, Ferrocote 5815, CAS: 64742-47-8, 64742-52-5

Results:

Summary:

Substrates:	Aluminum				
Contaminants:	Coatings				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Alconox Inc	Citranox	3	48.70	<input type="checkbox"/>	
Emkay Chemical Company	Safety Wash	25	56.70	<input type="checkbox"/>	
Emkay Chemical Company	Safety Wash CRC	25	65.60	<input type="checkbox"/>	
Emkay Chemical Company	Safety Wash Clear	25	60.50	<input type="checkbox"/>	
Savogran Company	SI #4 Coating Remover	100	79.20	<input type="checkbox"/>	
Twin Rivers Technologies	Methyl Ester 1618	100	83.60	<input checked="" type="checkbox"/>	

Conclusion: