

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 08/23/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Aluminum
 PartType: Coupon
 Contaminants: Coatings
 Cleaning Methods: Ultrasonics
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Coating, Ferrocoate 5815, CAS: 64742-47-8, 64742-52-5

Results:

Summary:

Substrates:	Aluminum				
Contaminants:	Coatings				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Savogran Company	HD-34 Cleaner Degreaser	50	75.80	<input type="checkbox"/>	
AG Environmental Products	Soy Gold 2000	25	85.70	<input checked="" type="checkbox"/>	
Chrisal USA Inc	Super CMF 240	15	99.50	<input checked="" type="checkbox"/>	
Emkay Chemical Company	Safety Wash CRC	25	98.20	<input checked="" type="checkbox"/>	
Emkay Chemical Company	Safety Wash Clear	25	95.20	<input checked="" type="checkbox"/>	

Conclusion: