

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 08/30/2001

Experimenters: Ravi Krishnappa

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Paints

Cleaning Methods: Ultrasonics

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Laboratory evaluation.  
Contaminant: Paint, Painter Touch Blue, CAS: 67-64-0, 1330-20-07

## Results:

### Summary:

<b>Substrates:</b>		Aluminum			
<b>Contaminants:</b>		Paints			
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Invista S.a.r.l	Flexisolv DBE 4 ester	100	103.50	<input type="checkbox"/>	
Twin Rivers Technologies	Methyl Ester 1618	100	86.70	<input checked="" type="checkbox"/>	

### Conclusion: