

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 09/27/2001  
 Experimenters: Ravi Krishnappa  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Mold Releases  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Laboratory evaluation.  
 Contaminant: Silicone, CAS: 63148-62-9, 7782-18-5, 9016-45-9, 9086-19-5

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel				
<b>Contaminants:</b>		Mold Releases				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>	
Brulin Corporation	Compliance	10	98.70	<input checked="" type="checkbox"/>		
Buckeye International	Shopmaster	5	89.90	<input checked="" type="checkbox"/>		
Mirachem Corporation	Mirachem 500	10	83.70	<input type="checkbox"/>		
Oakite Products	Inproclean 1300	10	96.40	<input checked="" type="checkbox"/>		
Sky Products Company Inc	Cleaner #10	10	85.90	<input checked="" type="checkbox"/>		
By Pas and Star Products	Star Cleaning Miracle # 50	10	96.60	<input checked="" type="checkbox"/>		
Simple Green	Simple Green D	10	98.50	<input checked="" type="checkbox"/>		
Magnaflux	Daraclean 283	10	97.80	<input checked="" type="checkbox"/>		

### Conclusion: