

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 10/02/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Adhesive
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Adhesive Ashland Acrylic Sealant 5504, CAS: 108-88-3, 141-78-6, 142-82-5, 67-63-0

Results:

Summary:

Substrates:		Stainless Steel				
Contaminants:		Adhesive				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	
Brulin Corporation	Compliance	10	-11.10	<input type="checkbox"/>		
Buckeye International	Shopmaster	5	-12.10	<input type="checkbox"/>		
Mirachem Corporation	Mirachem 500	10	-5.10	<input type="checkbox"/>		
Oakite Products	Inproclean 1300	10	-5.00	<input type="checkbox"/>		
Sky Products Company Inc	Cleaner #10	10	-18.00	<input type="checkbox"/>		
Simple Green	Simple Green D	10	-9.70	<input type="checkbox"/>		
By Pas and Star Products	Star Cleaning Miracle # 50	10	-8.20	<input type="checkbox"/>		
Magnaflux	Daraclean 283	10	-17.50	<input type="checkbox"/>		

Conclusion: