



CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 10/01/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Adhesive
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Contaminant: Adhesive Ashland Acrylic Sealant 5504, CAS: 108-88-3, 141-78-6, 142-82-5, 67-63-0

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Adhesive				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Brulin Corporation	Compliance	10	-11.10	<input type="checkbox"/>	
Buckeye International	Shopmaster	5	-12.10	<input type="checkbox"/>	
Mirachem Corporation	Mirachem 500	10	-5.10	<input type="checkbox"/>	
Oakite Products	Inproclean 1300	10	-5.00	<input type="checkbox"/>	
Sky Products Company Inc	Cleaner #10	10	-18.00	<input type="checkbox"/>	
Simple Green	Simple Green D	10	-9.70	<input type="checkbox"/>	
By Pas and Star Products	Star Cleaning Miracle # 50	10	-8.20	<input type="checkbox"/>	
Magnaflux	Daraclean 283	10	-17.50	<input type="checkbox"/>	

Conclusion: