

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 10/04/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Adhesive
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Adhesive Ashland Acrylic Sealant 5504, CAS: 108-88-3, 141-78-6, 142-82-5, 67-63-0

Results:

Summary:

Substrates:		Stainless Steel				
Contaminants:		Adhesive				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	
Invista S.a.r.l	Flexisolv DBE 4 ester	100	16.50	<input type="checkbox"/>		
Ensolve Biosystems Inc	Grease Feast Plus	5	4.10	<input type="checkbox"/>		
Transene Company, Inc.	D Greeze 500 LO	100	-3.80	<input type="checkbox"/>		
US Polychem Corporation	87 RB	100	4.50	<input type="checkbox"/>		
AW Chesterton	278 Super Solv	10	-9.70	<input type="checkbox"/>		
Bio Chem Systems	Bio T Max	100	26.60	<input type="checkbox"/>		
Bio Chem Systems	Bio T 300 B	5	2.24	<input type="checkbox"/>		
Warren Chemical Company	Sea Wash 8	5	6.64	<input type="checkbox"/>		

Conclusion: