

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 10/09/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Adhesive
 Cleaning Methods: Ultrasonics
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Adhesive Ashland Acrylic Sealant 5504, CAS: 108-88-3, 141-78-6, 142-82-5, 67-63-0

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Adhesive				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Invista S.a.r.l	Flexisolv DBE 4 ester	100	99.30	<input checked="" type="checkbox"/>	
Ensolve Biosystems Inc	Grease Feast Plus	5	6.60	<input type="checkbox"/>	
Bio Chem Systems	Bio T Max	100	48.20	<input type="checkbox"/>	
Bio Chem Systems	Bio T 300 B	5	9.42	<input type="checkbox"/>	
Warren Chemical Company	Sea Wash 8	5	9.63	<input type="checkbox"/>	

Conclusion: