

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 10/10/2001  
 Experimenters: Ravi Krishnappa  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Adhesive  
 Cleaning Methods: Ultrasonics  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Laboratory evaluation.  
 Contaminant: Adhesive Ashland Acrylic Sealant 5504, CAS: 108-88-3, 141-78-6, 142-82-5, 67-63-0

## Results:

### Summary:

|                         |                       |                 |                    |                                     |                      |  |
|-------------------------|-----------------------|-----------------|--------------------|-------------------------------------|----------------------|--|
| <b>Substrates:</b>      |                       | Stainless Steel |                    |                                     |                      |  |
| <b>Contaminants:</b>    |                       | Adhesive        |                    |                                     |                      |  |
| <b>Company Name:</b>    | <b>Product Name:</b>  | <b>Conc.:</b>   | <b>Efficiency:</b> | <b>Effective:</b>                   | <b>Observations:</b> |  |
| Invista S.a.r.l         | Flexisolv DBE 4 ester | 100             | 99.30              | <input checked="" type="checkbox"/> |                      |  |
| Ensolve Biosystems Inc  | Grease Feast Plus     | 5               | 6.60               | <input type="checkbox"/>            |                      |  |
| Bio Chem Systems        | Bio T Max             | 100             | 48.20              | <input type="checkbox"/>            |                      |  |
| Bio Chem Systems        | Bio T 300 B           | 5               | 9.42               | <input type="checkbox"/>            |                      |  |
| Warren Chemical Company | Sea Wash 8            | 5               | 9.63               | <input type="checkbox"/>            |                      |  |

### Conclusion: