

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 10/11/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Buffing/Polishing Compounds
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Buffing compound, Learok 2 B 111, CAS: 14808-60-7

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Buffing/Polishing Compounds				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Bio Chem Systems	Bio T Max	100	89.40	<input checked="" type="checkbox"/>	
Bio Chem Systems	Bio T 300 B	5	2.41	<input type="checkbox"/>	
Warren Chemical Company	Sea Wash 8	5	46.30	<input type="checkbox"/>	
Oakite Products	Inproclean 1300	10	50.40	<input type="checkbox"/>	
By Pas and Star Products	Star Cleaning Miracle # 50	10	-7.50	<input type="checkbox"/>	
US Polychem Corporation	87 RB	100	82.20	<input type="checkbox"/>	
Transene Company, Inc.	D Greeze 500 LO	100	75.40	<input type="checkbox"/>	

Conclusion: