

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001
 DateRun: 11/08/2001
 Experimenters: Ravi Krishnappa
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Lubricating/Lapping Oils
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Laboratory evaluation.
 Contaminant: Lubricant, Lubri Temp Anti Seize

Results:

Summary:

Substrates:		Stainless Steel			
Contaminants:		Lubricating/Lapping Oils			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Brulin Corporation	Compliance	10	-27.90	<input type="checkbox"/>	
AW Chesterton	278 Super Solv	10	14.50	<input type="checkbox"/>	
US Polychem Corporation	87 RB	100	93.70	<input checked="" type="checkbox"/>	
Bio Chem Systems	Bio T Max	100	88.60	<input checked="" type="checkbox"/>	
Transene Company, Inc.	D Greeze 500 LO	100	91.00	<input checked="" type="checkbox"/>	
Warren Chemical Company	Sea Wash 8	5	-40.60	<input type="checkbox"/>	
Ensolve Biosystems Inc	Grease Feast Plus	5	4.90	<input type="checkbox"/>	

Conclusion: