

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 11/07/2001  
 Experimenters: Ravi Krishnappa  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Lubricating/Lapping Oils  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Laboratory evaluation.  
 Contaminant: Lubricant, Lubri Temp Anti Seize

**Results:**

**Summary:**

<b>Substrates:</b>	Stainless Steel				
<b>Contaminants:</b>	Lubricating/Lapping Oils				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>
Brulin Corporation	Compliance	10	-27.90	<input type="checkbox"/>	
AW Chesterton	278 Super Solv	10	14.50	<input type="checkbox"/>	
US Polychem Corporation	87 RB	100	93.70	<input checked="" type="checkbox"/>	
Bio Chem Systems	Bio T Max	100	88.60	<input checked="" type="checkbox"/>	
Transene Company, Inc.	D Greeze 500 LO	100	91.00	<input checked="" type="checkbox"/>	
Warren Chemical Company	Sea Wash 8	5	-40.60	<input type="checkbox"/>	
Ensolve Biosystems Inc	Grease Feast Plus	5	4.90	<input type="checkbox"/>	

**Conclusion:**