

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001  
 DateRun: 11/29/2001  
 Experimenters: Ravi Krishnappa  
 ClientType: Lab  
 ProjectNumber: Project #1  
 Substrates: Stainless Steel  
 PartType: Coupon  
 Contaminants: Adhesive  
 Cleaning Methods: Immersion/Soak  
 Analytical Methods: Gravimetric  
 Purpose: Laboratory evaluations of alternative cleaning products  
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 i) 5 minute immersion cleaning with stir bar agitation @ 120 degree F.  
 (ii) 30 sec manual rinse with water @120 degree F.  
 (iii) air drying for about 24 hours.  
 CONTAMINANT INFO: Adhesive -Morstik 717- Rohm and Haas  
 CAS Numbers: 108-88-3, 110-54-3, 142-82-5, 67-63-0, 108-05-4

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel			
<b>Contaminants:</b>		Adhesive			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
EnviroSan Products Ltd	Solution 2000	10	7.10	<input type="checkbox"/>	
LPS Laboratories	Precision Clean Concentrate	10	14.60	<input type="checkbox"/>	
EcoLink	Heavy Weight Non Butyl Detergent	10	10.20	<input type="checkbox"/>	
Cleaning Systems	Release	10	13.40	<input type="checkbox"/>	
Ardrox Inc	6333	25	13.40	<input type="checkbox"/>	
Baum's Castorine Company Inc	EZE Oil-Grease Cleaner	25	18.50	<input type="checkbox"/>	

### Conclusion: