

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2001

DateRun: 12/31/2001

Experimenters: Purav Dave

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Cutting/Tapping Fluids

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min. immersion cleaning at 120 F with stir-bar agitation.  
Rinsing : 1/2 min manual in water at 120 F  
Drying : 1 min with heat gun at 500 F.  
Contaminants : Winfield Brooks - Alumtap.  
Cas # 64742-53-6, 127-18-4, 111-63-7.

## Results:

### Summary:

<b>Substrates:</b>		Aluminum			
<b>Contaminants:</b>		Cutting/Tapping Fluids			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Alconox Inc	Alcojet	1	82.08	<input type="checkbox"/>	
Buckeye International	Shopmaster FF	5	92.38	<input checked="" type="checkbox"/>	
Buckeye International	Shopmaster HP	5	92.05	<input checked="" type="checkbox"/>	
Buckeye International	Shopmaster LPH	5	89.92	<input checked="" type="checkbox"/>	
Calgon Corporation	SC 431	5	97.16	<input checked="" type="checkbox"/>	
Buckeye International	Immersion Cleaner	5	92.39	<input checked="" type="checkbox"/>	
Brulin Corporation	Aquavantage 1400	5	97.37	<input type="checkbox"/>	

### Conclusion: