

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002
 DateRun: 01/15/2002
 Experimenters: Heidi Wilcox
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Resins/Rosins
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F
 Rinsing: 1/2 min, manual, in 102 F water (tap)
 Drying: 1 min with heat gun @ 500F
 Contaminant: Solutia Inc, Gelva Multipolymer Resin Soln 2895
 CAS# 50862-469, resin solid ~ 40% by weight

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Resins/Rosins				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Kleer Flo Company	Grease Off 2	5	3.64	<input type="checkbox"/>	
Valtech Corporation	Valtron SP 2201	5	4.96	<input type="checkbox"/>	
Valtech Corporation	Valtron SP 2200	5	6.19	<input type="checkbox"/>	
International Products Corporation	LF 2100 (Liquid Foam Cleaner)	5	4.46	<input type="checkbox"/>	
US Polychem Corporation	Polychem PW 147	5	6.26	<input type="checkbox"/>	

Conclusion: None of the cleaners were effective.