

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002
 DateRun: 05/07/2002
 Experimenters: Purav Dave
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Latex binder
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: 5 min. immersion cleaning at 120 F. with stir-bar agitation.
 Rinsing: 1/2 min. manual with water at 120 F.
 Drying: 1 min. with heat gun at 500 F.
 Contaminant: latex Binder Mix,
 CAS#: 9016-45-, 79-06-1, 7664-41-7, 924-42-5, 50-00-0, 133386-4, 57-55-6, 7732-18-5

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Latex binder				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Kyzen Corporation	Ionox HC 2	100	46.89	<input type="checkbox"/>	
Safe Science Inc	Heavy Duty Kitchen Cleaner F1	5	54.42	<input type="checkbox"/>	
Safe Science Inc	Heavy Duty Kitchen Cleaner F2	5	33.32	<input type="checkbox"/>	
Sysco Corporation	Heavy Duty Kitchen Cleaner	5	57.28	<input type="checkbox"/>	
Dow Chemical Company	XUS 40570 Development Solvent	100	59.59	<input type="checkbox"/>	
Dow Chemical Company	XUS 40579 Development Solvent	100	54.60	<input type="checkbox"/>	
Oakite Products	Inproclean 61 B		36.25	<input type="checkbox"/>	Cocentration: 20.6g/ml
Oakite Products	Inproclean 2300		-6.03	<input type="checkbox"/>	Concentration: 426 g/l
Magnaflux	Daraclean 121	5	23.77	<input type="checkbox"/>	

Conclusion: None of the cleaners were effective.