

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002
 DateRun: 05/08/2002
 Experimenters: Purav Dave
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Latex binder
 Cleaning Methods: Ultrasonics
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Degasifying: 5 min. in ultrasonic crest at 120 F.
 Cleaning: 2 min. with ultrasonic agitation at 120 F.
 Rinsing: 1/2 min. manual with water at 120 F.
 Drying: 1 min. with heat gun at 500 F.
 Contaminant: Latex Binder Mix.
 CAS#: 9016-45-9, 79-06-1, 7664-41-7, 50-00-0, 57-55-6, 79-06-1, 924-42-5, 1333-86-4, 7732-18-5.

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Latex binder				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Kyzen Corporation	Ionox HC 2	100	104.68	<input type="checkbox"/>	
Safe Science Inc	Heavy Duty Kitchen Cleaner F1	5	100.84	<input checked="" type="checkbox"/>	
Safe Science Inc	Heavy Duty Kitchen Cleaner F2	5	100.75	<input checked="" type="checkbox"/>	
Sysco Corporation	Heavy Duty Kitchen Cleaner	5	95.51	<input checked="" type="checkbox"/>	
Dow Chemical Company	XUS 40570 Development Solvent	100	74.50	<input type="checkbox"/>	solvent remained on the coupons
Dow Chemical Company	XUS 40579 Development Solvent	100	55.54	<input type="checkbox"/>	
Magnaflux	Daraclean 121	5	99.95	<input checked="" type="checkbox"/>	
Oakite Products	Inproclean 61 B		85.98	<input checked="" type="checkbox"/>	concentration: 20.6 g/l
Oakite Products	Inproclean 2300		111.73	<input type="checkbox"/>	concentration: 426 g/l

Conclusion: