

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002
 DateRun: 05/30/2002
 Experimenters: Purav Dave
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Stainless Steel
 PartType: Coupon
 Contaminants: Coatings
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: 5 min. immersion cleaning at 120 F with stir-bar agitation.
 Rinsing: 1/2 min. manual with water at 120 F.
 Drying: 1 min. with heat gun at 500 F.
 Contaminant: Diversey: W.B. Filmite
 Paint Maskant

Results:

Summary:

Substrates:	Stainless Steel				
Contaminants:	Coatings				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
Kyzen Corporation	Ionox HC 2	100	102.31	<input checked="" type="checkbox"/>	
Safe Science Inc	Heavy Duty Kitchen Cleaner F1	5	94.61	<input checked="" type="checkbox"/>	
Safe Science Inc	Heavy Duty Kitchen Cleaner F2	5	61.63	<input type="checkbox"/>	
Sysco Corporation	Heavy Duty Kitchen Cleaner	5	88.98	<input checked="" type="checkbox"/>	
Dow Chemical Company	XUS 40570 Development Solvent	100	70.32	<input type="checkbox"/>	
Dow Chemical Company	XUS 40579 Development Solvent	100	99.32	<input checked="" type="checkbox"/>	
Oakite Products	Inproclean 61 B		97.53	<input checked="" type="checkbox"/>	Concentration: 20 g/l
Oakite Products	Inproclean 2300		97.14	<input checked="" type="checkbox"/>	Concentration: 20 g/l
Magnaflux	Daraclean 121	5	42.12	<input type="checkbox"/>	

Conclusion: