

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002

DateRun: 09/27/2002

Experimenters: Heidi Wilcox

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Greases

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 68 F  
Rinsing: 1/2 min, manual, in 68 F water (tap)  
Drying: 1 min with heat gun @ 500F  
Contaminant: Formax Manufacturing Corp, F-26 grease stick polishing lubricant (solid)  
CAS# 68815-16-7 Saponified stearic  
67701-27-3 Hydrofol glycerine  
64742-52-5 Mineral oil  
102-71-6 Emulsifying agent

Results: None of the cleaners were effective at ambient temperature. Will perform next trial with added heat, cleaners and rinse water will be at 120 F.

Summary:

<b>Substrates:</b>		Stainless Steel				
<b>Contaminants:</b>		Greases				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	
EcoLink	Bulldog	5	62.83	<input type="checkbox"/>		
Innovative Organics Inc	Amberclean Q3	5	27.34	<input type="checkbox"/>		
AG Environmental Products	Soy Clear 1500	100	-64.47	<input type="checkbox"/>		
AG Environmental Products	Canola Gold CE110	100	8.53	<input type="checkbox"/>		
Phase III Inc	California Parts Washer Solution	5	15.36	<input type="checkbox"/>		
PCI of America	Hurrisafe 9575	5	21.76	<input type="checkbox"/>		

Conclusion: