

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002

DateRun: 10/10/2002

Experimenters: Heidi Wilcox

ClientType: Lab

ProjectNumber: Project #1

Substrates: Aluminum

PartType: Coupon

Contaminants: Adhesive

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F  
Rinsing: 1/2 min, manual, in 102 F water (tap)  
Drying: 1 min with heat gun @ 500F  
Contaminant: Aroset PS 8078, Ashlan Chemical (Lot# 071901). Very thick adhesive  
CAS#'s 141-78-6 Ethyl Acetate, 142-82-5 Heptane, 67-63-0 Isopropanol

## Results:

### Summary:

<b>Substrates:</b>		Aluminum			
<b>Contaminants:</b>		Adhesive			
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:
EcoLink	Bulldog	5	10.65	<input type="checkbox"/>	
Innovative Organics Inc	Amberclean Q3	5	13.33	<input type="checkbox"/>	
AG Environmental Products	Soy Clear 1500	100	-53.60	<input type="checkbox"/>	
AG Environmental Products	Canola Gold CE110	100	-58.60	<input type="checkbox"/>	
Phase III Inc	California Parts Washer Solution	5	6.87	<input type="checkbox"/>	
PCI of America	Hurrisafe 9575	5	-2.45	<input type="checkbox"/>	

### Conclusion: