

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002
 DateRun: 10/14/2002
 Experimenters: Heidi Wilcox
 ClientType: Lab
 ProjectNumber: Project #1
 Substrates: Aluminum
 PartType: Coupon
 Contaminants: Adhesive
 Cleaning Methods: Immersion/Soak
 Analytical Methods: Gravimetric
 Purpose: Laboratory evaluations of alternative cleaning products
 Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
 Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F
 Rinsing: 1/2 min, manual, in 102 F water (tap)
 Drying: 1 min with heat gun @ 500F
 Contaminant: Aroset PS 8078, Ashlan Chemical (Lot# 071901). Very thick adhesive
 CAS#'s 141-78-6 Ethyl Acetate, 142-82-5 Heptane, 67-63-0 Isopropanol

Results:

Summary:

| | | | | | |
|---------------------------|----------------------|---------------|--------------------|--------------------------|----------------------|
| Substrates: | Aluminum | | | | |
| Contaminants: | Adhesive | | | | |
| Company Name: | Product Name: | Conc.: | Efficiency: | Effective: | Observations: |
| AG Environmental Products | Soy Gold 1000 | 100 | -113.51 | <input type="checkbox"/> | |
| EcoLink | Rip Tide | 10 | 1.69 | <input type="checkbox"/> | |

Conclusion: