

# CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2002

DateRun: 11/26/2002

Experimenters: Heidi Wilcox

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Greases

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.  
 Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 68 F  
 Rinsing: 1/2 min, manual, in 68 F water (tap) ambient  
 Drying: 1 min with heat gun @ 500F  
 Contaminant: Formax Manufacturing Corp, F-26 grease stick polishing lubricant (solid)  
 CAS# 68815-16-7 Saponified stearic  
 67701-27-3 Hydrofol glycerine  
 64742-52-5 Mineral oil  
 102-71-6 Emulsifying agent

## Results:

### Summary:

<b>Substrates:</b>		Stainless Steel				
<b>Contaminants:</b>		Greases				
<b>Company Name:</b>	<b>Product Name:</b>	<b>Conc.:</b>	<b>Efficiency:</b>	<b>Effective:</b>	<b>Observations:</b>	
Buckeye International	XL 100 Cleaner & Degreaser	5	98.61	<input checked="" type="checkbox"/>		
Buckeye International	Immersion Cleaner	5	100.05	<input checked="" type="checkbox"/>		
Buckeye International	Ambush	5	99.54	<input checked="" type="checkbox"/>		
SOQ Environmental Technology	Ecomate FN	5	97.33	<input checked="" type="checkbox"/>		
Simple Green	Concentrated Industrial Strength Cleaner and Degreaser	5	97.10	<input checked="" type="checkbox"/>		
Magnaflux	Daraclean 236	5	97.66	<input checked="" type="checkbox"/>		
Magnaflux	Daraclean 203	5	100.24	<input checked="" type="checkbox"/>		

### Conclusion: