

CLEANING LABORATORY EVALUATION SUMMARY

SCL #: 2003

DateRun: 04/01/2003

Experimenters: Heidi Wilcox

ClientType: Lab

ProjectNumber: Project #1

Substrates: Stainless Steel

PartType: Coupon

Contaminants: Adhesive

Cleaning Methods: Immersion/Soak

Analytical Methods: Gravimetric

Purpose: Laboratory evaluations of alternative cleaning products

Experimental Procedure: Basic cleaning performance testing was conducted using ASTM G122 as the bases for cleaning.
Cleaning: 5 min Immersion cleaning with stir-bar agitation @ 120 F
Rinsing: 1/2 min, manual, in 102 F water (tap)
Drying: 1 min with heat gun @ 500F
Contaminant: Ashland Chemical Acrylic sealant 5504
Cas# 108-88-3, 141-78-6, 142-82-5, 67-63-0

Results:

Summary:

Substrates:		Stainless Steel				
Contaminants:		Adhesive				
Company Name:	Product Name:	Conc.:	Efficiency:	Effective:	Observations:	
Florida Chemical Company	D-Limonene	100	99.75	<input checked="" type="checkbox"/>		
Bio Chem Systems	Bio T 300 B	100	99.92	<input checked="" type="checkbox"/>		
Brulin Corporation	Nature Sol 100	100	100.17	<input checked="" type="checkbox"/>		
AG Environmental Products	Soy Gold 1000	100	-14.05	<input type="checkbox"/>		
AG Environmental Products	Soy Gold 2000	100	-10.08	<input type="checkbox"/>		
AG Environmental Products	Soy Clear 1500	100	-16.15	<input type="checkbox"/>		
Vertec BioSolvents	VertecBio Gold Unscented Part Cleaner	100	4.76	<input type="checkbox"/>		
Finger Lakes Chemical	2-22 D Limonene Industrial Cleaner	100	0.47	<input type="checkbox"/>		

Conclusion: